KONGCRETE® INSTRUCTIONS BEFORE USE

Prior to use, please read and understand these instructions!

Please take the following safety measures before and during use:

! Wear protective gloves (provided in the kit) and safety glasses or goggles when mixing and pouring Kongcrete. Keep out of the reach of children!

! Kongcrete is for outside use only! Never use inside and use only as stated in these instructions.

Always keep Kongcrete kits at 65ºF - 75ºF (18ºC - 23ºC) for at least two hours before using. If the kits are used at lower temperatures, mixing time will be longer, the kits will take longer to set and will produce less volume. At higher temperatures, the kits will set much faster, lowering mixing and working time and will produce a higher volume, weaker composite.

Make sure your project is prepared properly before you mix and use Kongcrete!

Dig the hole to the right depth (60 cm - 90 cm). Put the post into the hole. Level the post and make sure it cannot move. If you use the Large Kit for more than one post, make sure all posts are prepared and the distance between the posts is not too far. Kongcrete will start to expand 25 seconds after mixing!

KONGCRETE® INSTRUCTIONS FOR USE

1 Remove the cap from the Large bottle and pour the contents of the small bottle into the large bottle. You can use the spout-cap to avoid spilling. (when using the spoutcap, squeeze the small bottle to accelerate the pouring)

2 Replace the cap back on the large bottle immediately and shake well for a maximum of 15 seconds. DO NOT EXCEED MIXING TIME AS BOTTLE MAY RUPTURE! Expansion starts 25 seconds after mixing.

3 Remove the cap immediately after mixing and pour the Kongcrete onto the post but evenly around the hole. The Kongcrete will expand and rise up and around the post and set hard in approximately 3 minutes.

4 After Kongcrete sets, any excess can be removed by cutting with a utility knife.